

# Unigloss

Code: 6726. ...

## ONE-PACK HIGH-QUALITY ENAMEL

- HIGH GLOSS FINISH
- HIGHEST QUALITY
- EXCELLENT LEVELLING

### CHARACTERISTICS

One-pack alkyd-urethane finish. High quality, excellent dilatation and optimum colour and gloss retention. Suitable for use outside and inside pleasure crafts and houses. This product is very flexible and adheres well to a wide range of primers, undercoats and finishes. It cannot be directly applied to inorganic zinc primers or to galvanised panels. Available in various colours. Not suitable for continuous immersion.

- \* WHITE AND LIGHT COLOURS: s.w. 1,20 +/- 0,02 kg/l
- \* OTHER COLOUR: s.w. 1,05 +/- 0,05 kg/l

### TECNICAL DATA

Curing mechanism:	thinner evaporation and chemical reaction
Specific weight:	1.20* ± 0,02 Kg/L
Solid By Volume:	55 %
Flash Point:	+37 °C
Appearance:	glossy
Colour:	see colour chart
Packaging:	0,75 litres (only white 2,50 litres)

### SURFACE PREPARATION

Apply to surfaces which have already been primed or to old paint in good condition which has been sanded, dried and cleaned and which is free from oil, grease and other contaminants.  
Sand with 300/600 grade abrasive paper to obtain a smooth surface.

### APPLICATION

Stir the paint thoroughly until the colour is homogeneous. The excellent levelling properties of this paint produce glossy, mirror-like surfaces, even when applied with a brush. For a perfect finish apply 2 coats of Unigloss.

If applied with brush or roller up to 5% by volume of thinner 6470 can be added, up to 15% if applied with a spray-gun. Apply an even and fully wet coat by using cross-strokes in order to obtain full coverage.

# Unigloss

Code: 6726. ...

## ONE-PACK HIGH-QUALITY ENAMEL

### APPLICATION DATA

Drying time before use (20 °C):	7 days
Pot Life (20 °C):	/
Application temp. min/ max:	+5/+35 °C
Hardener:	/
Mixing ratio by volume:	/
Mixing ratio by weight:	/
Thinner/Thinner for cleaning:	6470
Wet film thickness per coat:	80 µ
Dry film thickness per coat:	40 µ
Theoretical coverage per coat:	13,8 m <sup>2</sup> /L
Minimum covering time (20 °C):	24 hours
Maximum covering time (20 °C):	/
Number of coats:	2

### NOTES

Spray application data	Conventional	Airless
Fluid tip orifice	1,2/1,4 mm.	
Air pressure	2,0/3,0 atm.	
Compression ratio		

### SAFETY RULES

Adequate ventilation must be provided when applying this product in a confined area and during the subsequent drying period. The product contains solvents which could form an explosive mixture when combined with air and exposed to a naked flame, spark or electrostatic discharge. The wearing of goggles, masks, gloves and protective clothing is recommended. Before use read the sections 7-8 of the Safety Data Sheet (MSDS).  
**INSTRUCTIONS FOR THE SAFE BIOCIDAL PRODUCT DISPOSAL AND PACKAGING**  
 Empty packaging having contained biocidal products: empty packaging shall be disposed of in compliance to provisions required by the law on disposal of said waste, for example by consignment to a recycling centre.  
 Packaging containing unused biocidal product: the unused product shall be disposed of in compliance to provisions required by the law on disposal of said waste, for example by consignment to a recycling centre, in this case it is forbidden to recycle packaging. Do not empty into drains and watercourses. The paint cans must not be stocked outside and must be stored at a temperature between 10 ° C and 35 ° C. Do not expose to the sun.

**DISCLAIMER** The information in this data sheet is based on accurate laboratory tests and practical experience, which guarantee the quality of the product if used according to our recommendations. The data contained herein are liable to modification as a result of continuous product development. We do not accept any liability arising from use not in accordance with our recommendations, unless authorized specifically by the Veneziani Technical Services. This edition annuls and replaces all previous issues.