

AquaStrip

Code: 6040.672

WATER BASED STRIPPER FOR ANTIFOULINGS

- REMOVES OLD ANTIFOULINGS
- DOES NOT DAMAGE GEL COATS
- WATER BASED
- ENVIROMENTALLY FRIENDLY
- NON SAGGING

CHARACTERISTICS

Ecological water based stripping gel with low enviromental impact solvents. Specifically formulated for removing old antifoulings from wood, GRP, steel and other metals. It has good stripping power also on one-pack primers, undercoats and finishes. Being water-based it does not damage gel coats or GRP and can be handled without harmor risk. AquaStrip requires longer softening time if compared to solvent based strippers, but is effective on large surfaces such as hulls applying one coat only without any danger for the boat, the operators and the environment. AquaStrip free from toxic or harmful components: does not contain N-methyl-2-pyrrolidone (NMP). Has a neutral pH and can be used indoors without requiring special ventilation.

Caution: store between 5 to 35° C.

TECNICAL DATA

Curing mechanism:	/
Specific weight:	1,00-1,2 kg/lit ± 0,02
Solid By Volume:	
Flash Point:	<21 °C
Appearance:	/
Colour:	light green
Packaging:	2,5 litres

SURFACE PREPARATION

Wash surfaces to be stripped with fresh water and let dry. Do not apply AquaStrip on wet surfaces.

APPLICATION

Homogeinize the product before use.

Apply one even coat of AquaStrip with brush to the surface to be stripped. Let the product work and make sure that the surface does not dry. Remove the softened layer with a spatula. The time necessary for softening depends on the thickness and the type of paint and may vary from a minimum of 2 hours to a maximum of 12 hours. If there are several layers to be removed, wait for a longer time or, if necessary, repeat the whole operation.

The softened paint may be removed also by high pressure washing. Washing until all traces of stripper are removed and/or degrass. Allow to dry thoroughly before painting again the surface.

Aquastrip

Code: **6040.672**

WATER BASED STRIPPER FOR ANTIFOULINGS

APPLICATION DATA

Drying time before use (20 °C):	/
Pot Life (20 °C):	/
Application temp. min/ max:	+5/+35 °C
Hardener:	/
Mixing ratio by volume:	/
Mixing ratio by weight:	/
Thinner/Thinner for cleaning:	lcool ou solvant Alcohol - Solvent
Wet film thickness per coat:	
Dry film thickness per coat:	/
Theoretical coverage per coat:	2 - 3 m ² /L
Minimum covering time (20 °C):	/
Maximum covering time (20 °C):	/
Number of coats:	/

NOTES

SAFETY RULES

The use of gloves and protective clothing is recommended. In case of prolonged skin contact, wash thoroughly with water. The product does not require EEC labelling. Before use read the sections 7-8 of the Safety Data Sheet (MSDS).
INSTRUCTIONS FOR THE SAFE BIOCIDAL PRODUCT DISPOSAL AND PACKAGING
 Empty packaging having contained biocidal products: empty packaging shall be disposed of in compliance to provisions required by the law on disposal of said waste, for example by consignment to a recycling centre.
 Packaging containing unused biocidal product: the unused product shall be disposed of in compliance to provisions required by the law on disposal of said waste, for example by consignment to a recycling centre, in this case it is forbidden to recycle packaging. Do not empty into drains and watercourses. The paint cans must not be stocked outside and must be stored at a temperature between 10 ° C and 35 ° C. Do not expose to the sun.

DISCLAIMER The information in this data sheet is based on accurate laboratory tests and practical experience, which guarantee the quality of the product if used according to our recommendations. The data contained herein are liable to modification as a result of continuous product development. We do not accept any liability arising from use not in accordance with our recommendations, unless authorized specifically by the Veneziani Technical Services. This edition annuls and replaces all previous issues.